

SELECTION 13M 580-650°C

High resistant metallic glass colors

1. General Information and Color chart

Features!

- High resistant and intensive colors.
- Intermixable with SELECTION 13 colors.
- Glitter interference colors available.



Technical Information

Revised: 10/27/2024

SELECTION 13M 580–650°C High resistant, metallic and interference metallic glass colors for bottles, cosmetic containers and glass tableware.

Table 1

Product No.	Color tone	Pantone No. / interference color on 13706 black	Intermixable	Lead free (below 90ppm)	Cadmium free (below 40ppm)	Acid resistant, DIN 1388-1-2 *1	Alkali resistant, ASTM C556-88 *2	Glass	P.S.D. D ₅₀ (average μ m)	P.S.D. D ₁₀₀ (biggest μ m)	Printing mesh size (mesh/inch, thread/cm)	Remarks
Metallic colors												
13M11	white silver		✓	✓	✓	✓	✓	9-11	55	195, 77T		fine particle size, white silver, can mix with all of SELECTION 13 colors
13M48	white silver		✓	✓	✓	✓	✓	15-20	150	195, 77T		white silver, can mix with all of SELECTION 13 colors
13M49	lemon gold	8640C	✓	✓	✓	✓	✓	9-11	55	195, 77T		greenish gold
13M2	lemon gold	8641C	✓	✓	✓	✓	✓	20-22	135	195, 77T		lemon gold
13M15	orange gold	871C	✓	✓	✓	✓	✓	9-11	55	195, 77T		orange gold
13M3	copper	876C	✓	✓	✓	✓	✓	9-11	55	195, 77T		
13M5	red copper	8903C	✓	✓	✓	✓	✓	9-11	55	195, 77T		
Interference metallic colors												
13M24	orange gold	-8660C	✓	✓	✓	✓	✓	9-11	55	195, 77T		
13M28	yellow green	-8703C	✓	✓	✓	✓	✓	13-20	105	195, 77T		
13M29	green	-8323C	✓	✓	✓	✓	✓	9-11	55	195, 77T		
13M34	blue	-8132C	✓	✓	✓	✓	✓	9-11	55	195, 77T		
13M37	blue	-8133C	✓	✓	✓	✓	✓	9-11	55	195, 77T		
13M38	lilac	-8103C	✓	✓	✓	✓	✓	9-11	55	195, 77T		
13M41	red	-8063C	✓	✓	✓	✓	✓	9-11	55	195, 77T		
13M60	silver	-	✓	✓	✓	✓	✓	70-90	420	103, 40T		glitter interference colors, firing lower than 580°C is recommended
13M62	gold	-	✓	✓	✓	✓	✓	45-55	420	103, 40T		glitter interference colors, firing lower than 580°C is recommended
13M63	blue green	-	✓	✓	✓	✓	✓	45-55	420	103, 40T		glitter interference colors, firing lower than 580°C is recommended
13M64	red	-	✓	✓	✓	✓	✓	45-55	420	103, 40T		glitter interference colors, firing lower than 580°C is recommended
Special colors for SELECTION 13M colors												
13111	flux		✓	✓	✓	✓	✓	4-5	20-30	260, 100T		mixing flux
13212	white		✓	✓	✓	✓	✓	4-5	20-30	260, 100T		underlay white
13706	black	process blackC	✓	✓	✓	✓	✓	4-5	20-30	260, 100T		underlay black

*1: DIN EN 1388-1-2 : The test pieces are immersed in a 4% acetic acid solution for 24 hours at 22±2°C. Refer section 7.2 and 7.3

*2: ASTM C556-88 : The test pieces are immersed in a 0.5 % sodium carbonate solution in water at 95°C for 2, 4 and 6 hours. Refer section 7.4

2. Firing Conditions

Normal firing is from 580–650°C in a cycle of 60–150 minutes, cold-to-cold, with 10 minutes for soaking. The best firing condition depends on firing speed and type of ware and kiln.

13M60, 13M62, 13M63 and **13M64** are very sensitive for firing temperature and conditions. We recommend to fire them below 620°C, otherwise they may lose metallic effect.

3. Application

SELECTION 13M metallic colors are suitable for screen-transfer printing, direct printing, spraying, pad printing and hand painting.

4. Coefficient of Thermal Expansion (C.O.E.)

Product	Thermal Expansion (C.O.E.)
SELECTION 13M metallic colors (average)	Varies between $8.5\text{--}9.5 \times 10^{-6}/^{\circ}\text{C}$
SELECTION 13 colors (average)	Varies between $8.5\text{--}9.0 \times 10^{-6}/^{\circ}\text{C}$
13111 flux	$8.5 \times 10^{-6}/^{\circ}\text{C}$

If **SELECTION 13M** metallic colors are applied in very thick layers, the colors could crack or chip off, depending on the type of ware and thickness of the colors. We recommend you test the application of the colors under your conditions before use.

5. Particle size of Distribution (P.S.D.) and Printing

【5.1 Particle size】

13M60, 13M62, 13M63 and **13M64** are coarse particle size than other colors. As for each color particle size, please refer to Table 1. Recommended mesh size to print is below.

【5.2 Medium ratio and Mesh size】

Product	Color : medium	Recommended mesh size
SELECTION 13M normal colors : Medium PM2	10 : 7–10	195 mesh/inch, 77 thread/cm
13M60, 13M62, 13M63 and 13M64 : Medium PM2	10 : 7–10	103 mesh/inch, 40 thread/cm
SELECTION 13 colors : Medium PM2	10 : 5–7	195–305 mesh/inch (77–120 thread/cm)
13111 flux : Medium PM2	10 : 5.5–8	195–305 mesh/inch (77–120 thread/cm)

Screen-transfer printing: We recommend PM2 flowing medium. We recommend C12 cover coat by printing 70 mesh/inch (27 thread/cm).

If the ink is not a good homogeneous paste, the metallic colors will be dried easily on the screen during printing and, after firing, their surface and gloss will become not smooth and worse. In this case we recommend adding a little more medium to get a better homogenous of paste.

Glass colors absorb any moisture easily. Therefore, keep powder colors in a dry place. We recommend drying the color powder before using.

6. Color and Mixability

SELECTION 13M metallic colors can be mixed with each other in any proportions. Mixing with other **SELECTION 13** colors can be developed a wide range of metallic effect colors. However, we recommend testing the stability of mixing colors under end-user's firing conditions before mass production. Please note the following recommendations.

Mixing white silver: To obtain colored metallic, it is suitable to mix **13M11** or **13M48** white silver with approximate 15–30% of **SELECTION 13** colors. To make gray silver tone, mixing **13M11** or **13M48** white silver with **13706** black is recommended. Cadmium-containing colors, **13313** yellow, **13318** orange, **13412** green **13628** and **13634** red also can be mixed with **SELECTION 13M** metallic colors.

Underlay colors: Any of **SELECTION 13** colors can be printed as underlay colors. **13706** black and **13212** white are recommended as underlay colors for both metallic and interference metallic colors to get intensive effect. If the underlay colors are over fired, especially interference metallic colors, they lose the metallic effect. In this case, we recommend firing lower.

Mixing flux: **13111** flux is recommended to mix with **SELECTION 13M** metallic colors to lighten the colors. According to our experience, maximum 30% of additional flux is allowed.

Overprinting flux: We do not recommend printing **13111** flux on **SELECTION 13M** metallic colors. If printed on **SELECTION 13M** colors, they may lose metallic effect.

Glitter interference colors: **13M60**, **13M62**, **13M63** and **13M64** are glitter interference metallic colors. They can be mixed with each other's and with other metallic colors. They are sensitive for firing temperature and we recommended to fire them below 650 °C not to lose their color intensity.

7. Chemical durability (refer to the Table 1)

Chemical durability of **SELECTION 13M** metallic colors depends on type of ware, kiln, color deposit and firing conditions. The following are the results of tests on soda lime glass, fired at 620°C, with 10 minutes of soaking time and 120 minutes of cold-to-cold firing conditions of gas kiln in production.

【7.1 Lead and cadmium release】

According to the DI EN 1388-1-2 test, **SELECTION 13M** metallic colors show less than lead 0.8 mg/dm² and cadmium 0.07 mg/dm² releases.

【7.2 Acid resistance】

According to the DI EN 1388-1-2 test, **SELECTION 13M** metallic colors do not show any visible attack after immersion in a 4% acetic acid solution for 24 hours at a room temperature of 22±2°C.

【7.3 Alkali resistance】

According to the ASTM C556-88 test, **SELECTION 13M** metallic colors do not show any visible attack for up to 4 hours.

8. Safety Data Sheet (SDS)

Safety data sheet (SDS) of **SELECTION 13M** metallic colors are available on request.

The above information and statements are unsolicited. IZAWA PIGMENT CO., LTD. provides them to promote its products. The above information and statements are also believed to be accurate at the time of publication under their laboratory conditions. Use of them is at the sole discretion of the user and IZAWA PIGMENT CO., LTD. does not give any warranty with respect to any test results. In no event shall IZAWA PIGMENT CO., LTD. be liable for any direct, indirect, special, incidental, or consequential damages arising out of the use of the above information.